

# X7R Dielectric

## Specifications and Test Methods



Parameter/Test		X7R Specification Limits	Measuring Conditions	
<b>Operating Temperature Range</b>		-55°C to +125°C	Temperature Cycle Chamber	
<b>Capacitance</b>		Within specified tolerance		
<b>Dissipation Factor</b>		$\leq 10\%$ for $\geq 50V$ DC rating $\leq 12.5\%$ for 25V DC rating $\leq 12.5\%$ for $\leq 10V$ DC rating Contact Factory for DF by PN	Freq.: 1.0 kHz $\pm 10\%$ Voltage: 1.0Vrms $\pm .2V$ For Cap > 10 $\mu$ F, 0.5Vrm @ 120Hz	
<b>Insulation Resistance</b>		10,000M $\Omega$ or 500M $\Omega$ - $\mu$ F, whichever is less	Charge device with rated voltage for 120 $\pm$ 5 secs @ room temp/humidity	
<b>Dielectric Strength</b>		No breakdown or visual defects	Charge device with 250% of rated voltage for 1-5 seconds, w/ charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.	
<b>Resistance to Flexure Stresses</b>	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds	
	Capacitance Variation	$\leq \pm 12\%$		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3		
<b>Solderability</b>		$\geq 95\%$ of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 $\pm$ 5°C for 5.0 $\pm$ 0.5 seconds	
<b>Resistance to Solder Heat</b>	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 $\pm$ 2 hours before measuring electrical properties.	
	Capacitance Variation	$\leq \pm 7.5\%$		
	Dissipation Factor	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
<b>Thermal Shock</b>	Appearance	No visual defects	Step 1: -55°C $\pm 2^\circ$	30 $\pm$ 3 minutes
	Capacitance Variation	$\leq \pm 7.5\%$	Step 2: Room Temp	$\leq 3$ minutes
	Dissipation Factor	Meets Initial Values (As Above)	Step 3: +125°C $\pm 2^\circ$	30 $\pm$ 3 minutes
	Insulation Resistance	Meets Initial Values (As Above)	Step 4: Room Temp	$\leq 3$ minutes
	Dielectric Strength	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 $\pm$ 2 hours at room temperature	
<b>Load Life</b>	Appearance	No visual defects	Pre-treatment: After mounting, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure.  Charge device with $\geq$ rated voltage in test chamber set at 125°C $\pm 2^\circ$ C for 1000 hours (+48, -0).  Pre-treatment: After remove from test chamber, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure.  Contact KYOCERA AVX for datasheet of specific parts.	
	Capacitance Variation	$\leq \pm 12.5\%$		
	Dissipation Factor	$\leq$ Initial Value x 2.0 (See Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
<b>Load Humidity</b>	Appearance	No visual defects	Pre-treatment: After mounting, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure.  Store in a test chamber set at 85°C $\pm 2^\circ$ C/ 85% $\pm 5\%$ relative humidity for 1000 hours (+48, -0) with rated voltage applied.  Pre-treatment: After remove from test chamber, perform heat treatment 150+0/-10C for 2 hour, then stabilise for 24+/-2 hour at room temp, then measure.	
	Capacitance Variation	$\leq \pm 12.5\%$		
	Dissipation Factor	$\leq$ Initial Value x 2.0 (See Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		

# X7R Dielectric Capacitance Range



## PREFERRED SIZES ARE SHADED

SIZE	0101*		0201				0402				0603						0805						1206																		
	Reflow Only		Reflow Only				Reflow/Wave				Reflow/Wave						Reflow/Wave						Reflow/Wave																		
Soldering	Paper/ Embossed		All Paper				All Paper				All Paper						Paper/Embossed						Paper/Embossed																		
(L) Length	mm	0.40 ± 0.02	0.60 ± 0.03				1.00 ± 0.10				1.60 ± 0.15						2.01 ± 0.20						3.20 ± 0.30																		
(W) Width	mm	0.20 ± 0.02	0.30 ± 0.03				0.50 ± 0.10				0.81 ± 0.15						1.25 ± 0.20						1.60 ± 0.30																		
(t) Terminal	mm	0.10 ± 0.04	0.15 ± 0.05				0.25 ± 0.15				0.35 ± 0.15						0.50 ± 0.25						0.50 ± 0.25																		
WVDC		16	6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	500			
Cap 100 101	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
Cap 150 151	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
220 221	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J	E	E	E	E	E	E	E	E	J	J	J	J	J	J	J	J	J		
330 331	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
470 471	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
680 681	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
1000 102	B	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
1500 152	A	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
2200 222	A	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
3300 332	A	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
3900 392	A	A	A	A	A	A																																			
4700 472	A	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
5600 562	A	A	A	A	A	A																																			
6800 682	A	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
Cap 0.01 103	A	A	A	A	A	A	C	C	C	C	C	C	C	G	G	G	G	G	G	G	J	J																			
(µF) 0.012 123																																									
0.015 153							C	C	C	C	C	E																													
0.018 183																																									
0.022 223		A	A	A			C	C	C	C	E																														
0.027 273																																									
0.033 333							C	C	C	C	E																														
0.039 393																																									
0.047 473							C	C	C	C	E																														
0.068 683							C	C	C	C	E																														
0.082 823																																									
0.1 104		A					C	C	C	C	E																														
0.12 124																																									
0.15 154														G	G	G	J	J																							
0.22 224							C	C	C	C					G	G	J	J	J																						
0.33 334														J	J	J	J	J																							
0.47 474							C	C						J	J	J	J	J																							
0.68 684														J	J	J							P	P	P																
1.0 105							C							J	J	J	J	K																							
2.2 225														J	J	K							P	P	P	P															
4.7 475														K									P	P	P																
10 106																							P	P	P																
22 226																																									
47 476																																									
100 107																																									
WVDC		16	6.3	10	16	25	50	6.3	10	16	25	50	100	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	6.3	10	16	25	50	100	200	250	500			
SIZE		0101*	0201				0402				0603						0805						1206																		

Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)
	PAPER						EMBOSSSED							

NOTE: Contact factory for non-specified capacitance values  
 \*EIA 01005  
 \*\*Contact Factory for Specifications

# X7R Dielectric Capacitance Range



## PREFERRED SIZES ARE SHADED

SIZE	1210							1812					1825			2220				2225				
Soldering	Reflow Only							Reflow Only					Reflow Only			Reflow Only				Reflow Only				
Packaging	Paper/Embossed							All Embossed					All Embossed			All Embossed				All Embossed				
(L) Length	3.30 ± 0.4 (0.130 ± 0.016)							4.50 ± 0.40 (0.177 ± 0.016)					4.50 ± 0.40 (0.177 ± 0.016)			5.70 ± 0.50 (0.224 ± 0.020)				5.70 ± 0.40 (0.224 ± 0.016)				
(W) Width	2.50 ± 0.30 (0.098 ± 0.012)							3.20 ± 0.40 (0.126 ± 0.016)					6.40 ± 0.40 (0.252 ± 0.016)			5.00 ± 0.40 (0.197 ± 0.016)				6.30 ± 0.40 (0.248 ± 0.016)				
(t) Terminal	0.50 ± 0.25 (0.020 ± 0.010)							0.61 ± 0.36 (0.024 ± 0.014)					0.61 ± 0.36 (0.024 ± 0.014)			0.64 ± 0.39 (0.025 ± 0.015)				0.64 ± 0.39 (0.025 ± 0.015)				
WVDC	10	16	25	50	100	200	500	16	25	50	100	200	500	50	100	200	25	50	100	200	500	50	100	200
Cap 100 101																								
(pF) 150 151																								
220 221				K	K	K	M																	
330 331				K	K	K	M			N	N	N	N											
470 471				K	K	K	M			N	N	N	N											
680 681				K	K	K	M			N	N	N	N											
1000 102	K	K	K	K	K	K	M	N	N	N	N	N	N	X	X	X	X	X	X	X	X	X	X	X
1500 152	K	K	K	K	K	K	M	N	N	N	N	N	N	X	X	X	X	X	X	X	X	X	X	X
2200 222	K	K	K	K	K	K	M	N	N	N	N	N	N	X	X	X	X	X	X	X	X	X	X	X
3300 332	K	K	K	K	K	K	P	N	N	N	N	N	N	X	X	X	X	X	X	X	X	X	X	X
4700 472	K	K	K	K	K	K	P	N	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X	X
6800 682	K	K	K	K	K	K	P	N	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X	X
Cap 0.01 103	K	K	K	K	K	K	P	N	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X	X
(µF) 0.015 153	K	K	K	K	K	K	P	N	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X	X
0.022 223	K	K	K	K	K	K	P	Q	N	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X
0.033 333	K	K	K	K	K	K	P	X	N	N	N	N	N	X	X	X	X	X	X	X	X	X	X	X
0.047 473	K	K	K	K	K	K	P	X	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X	X
0.068 683	K	K	K	K	K	K	P	X	N	N	N	N	P	X	X	X	X	X	X	X	X	X	X	X
0.1 104	K	K	K	K	K	K	P	X	N	N	N	P	P	X	X	X	X	X	X	X	X	X	X	X
0.15 154	K	K	K	K	M	P	Z	Z	N	N	N	P	P	Z	X	X	X	X	X	X	X	X	X	X
0.22 224	K	K	K	M	P	Z			N	N	N	P	Q	Z	X	X	X	X	X	X	X	X	X	X
0.33 334	K	K	K	M	Q	Z			N	N	N	P	X	Z	X	X	X	X	X	X	X	X	X	X
0.47 474	M	M	M	P	Q	Z			N	N	N	Q	X	Z	X	X	X	X	X	X	X	X	X	X
0.68 684	M	M	P	X	X	Z			Q	Q	Q	Q	Z		X	X	X	X	X	X	Z	X	X	X
1.0 105	P	P	P	X	Z				Q	Q	Q	X	Z		X	X	X	X	X	X	7	X	X	X
1.5 155	N	N	Z	Z	Z				Z	Z	Z				X	X	Z	X	X	Z		X	X	Z
2.2 225	X	X	Z	Z	Z				Z	Z	Z				X	X	Z	X	X	Z		X	X	Z
3.3 335	X	X	Z	Z	Z				Z	Z	Z				X	X					X	Z		
4.7 475	Z	Z	Z	Z	Z				Z	Z	Z				X	X					Z	Z		
10 106	Z	Z	Z	Z				Z	Z	Z				Z	Z					Z	Z		Z	
22 226	Z	Z	Z																		Z			
47 476	Z																							
100 107																								
WVDC	10	16	25	50	100	200	500	16	25	50	100	200	500	50	100	200	25	50	100	200	500	50	100	200
SIZE	1210							1812					1825			2220				2225				



Letter	A	B	C	E	G	J	K	M	N	P	Q	X	Y	Z	7
Max. Thickness	0.33 (0.013)	0.22 (0.009)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)	3.30 (0.130)
	PAPER						EMBOSSSED								

NOTE: Contact factory for non-specified capacitance values

# Mouser Electronics

Authorized Distributor

Click to View Pricing, Inventory, Delivery & Lifecycle Information:

## AVX:

[08051X471KSJME](#) [1206CA681MAJ1A](#) [08051C153KAT4H](#) [08051C222KAT4H](#) [0201YC681K](#) [08051C561JAT4H](#)  
[08052C102JAT4H](#) [08052C561JAT4H](#) [12065X222MAT2A](#) [05045C102KA79A](#) [05045C471KA19A](#) [05045C472MAT1A](#)  
[08051X102KS19A](#) [08051X102KSJ9A](#) [08051X102KSJME](#) [08051X121KSJ9A](#) [08051X221KSJ9A](#) [08055X103KSJ9A](#)  
[08055X103KSJME\2K](#) [08055X153KSJ9A](#) [12061X103KSJ9A](#) [12063C564KA76N](#) [12065C682KHT1A](#)  
[12065C683KHT1A](#) [1206YC105MA76N](#) [12105X104KS19A](#) [12105X104MSJME](#) [12105X473KSJME\1K](#)  
[18051X103KSJ9A](#) [18121X473KSJME](#) [18125X104KSJ9A](#) [18251X104KSJ9A](#) [18255X474KSJ9A](#) [05045C102KA11A](#)  
[22251C105K/BULK](#) [22251E225ZA1M6](#) [22251E225ZA116](#) [05041C151KAT1A](#) [05045C101KA11A](#) [05045C101KA79A](#)  
[05045C102KAT9A](#) [05045C102KA71A](#) [05045C102KA76A](#) [05045C102MAT9A](#) [05045C103JAT1A](#) [05045C103JA11A](#)  
[05045C103JA16A](#) [05045C103KA11A](#) [05045C103KA19A](#) [05045C103KA76A\100](#) [05045C103MAT1A](#)  
[05045C103MA71A](#) [05045C103MA79A](#) [05045C121KAT1A](#) [05045C122JAT9A](#) [05045C151KAT1A](#) [05045C152JAT1A](#)  
[05045C152JHT6A](#) [05045C152KA79A](#) [05045C152MA79A](#) [05045C181KAT1A](#) [05045C182KAT1A](#) [05045C221KAT1A](#)  
[05045C221KA79A](#) [05045C222JAT1A](#) [05045C222JA16A](#) [05045C331KAT1A](#) [05045C332JA16A](#) [05045C332KAT1A](#)  
[05045C332KA79A](#) [05045C391KAT1A](#) [05045C392JA16A\H](#) [05045C392KAT1A](#) [05045C471KA79A](#) [05045C472JA16A](#)  
[05045C472JA19A\H](#) [05045C472KAT1A](#) [05045C472KA16A](#) [05045C561JA19A\H](#) [05045C561KAT1A](#)  
[05045C562KAT1A](#) [05045C681KAT1A](#) [05045C681KA11A](#) [05045C681KA79A](#) [05045C682JA19A\H](#)  
[05045C682KAT1A](#) [08053C104KGT1A](#) [08053C104KGT6A](#) [12061X103KSJME\1K](#) [0805ZC105JAJ9A](#)  
[08051X102KSJME\1K](#) [08051X222KSJ9A](#) [12105X104MSJME\1K](#) [08051X332KST9A](#) [18255X334KSJ9A](#)  
[06031C103JA76N](#) [08051X102KS1WE](#) [08055X103KS19A](#) [08055X472KSJ9A](#) [18122C104KAJ9A](#)